



## PRODUCT DATA

### SUPERIORCOTE E-FLEX

Class-leading, elastomeric coating designed to bridge hairline cracking in stucco or masonry substrates leaving a durable flat finish. Formulated with 100% pure acrylic elastomeric polymers, SuperiorCote E-Flex dries to a stretchy rubber-like film on the surface yet is vapor permeable.

#### FEATURES & BENEFITS

- Bridges minor hairline cracks in stucco and masonry
- Waterproof - resists wind-driven rain
- Vapor Open - resists blistering
- Flat finish
- 100% Acrylic Polymers for durability
- Highly Flexible
- Water-based - easy clean up with water

Application Temperature: 40° -110°F (5° -43°C)

Dry to Touch: 2-4 hours at room temperature

Recoat Time: 8 hours at room temperature

Dry Time: 12 hours at room temperature

#### JOB CONDITIONS

Air and substrate temperature for application of SuperiorCote E-Flex must be 40°F (5°C) or higher and must remain 40°F (5°C) or higher for a minimum of 24 hours. Provide temporary protection to protect the wall system from damage until permanent flashings, caps and sealants are installed. Store materials within prescribed temperature limits and out of direct sunlight. High temperatures will reduce working times, Low temperatures and/or high humidity and pigment loading will extend working, set and dry times.

#### PREPARATION

Surface temperature must be above 40°F (5°C). Surface must be clean, dry, structurally sound and free of efflorescence, oil, grease, form release agents, and curing compounds. On previously painted surfaces, all loose, peeling and chalking paint must be removed. Any glossy areas must be sanded.

Concrete – Must have cured a minimum of 28 days prior to the application of SuperiorCote E-Flex. If form release agents or curing compounds exist on the surface, they must be removed with an appropriate solution. Remove any residual solution by flushing with water.

Masonry – Clean, cured, dry.

Stucco – Must be cured, dry. If additives were used in the stucco, it is recommended that a test patch be made to evaluate bond strength of the SuperiorCote E-Flex to the stucco.

#### Coverage per pail (sf/m<sup>2</sup>)\*

One Coat: 375-400 sf/pail (34-37 sm)

Two Coat: 187-200 sf/pail (17-18.5 sm)

*\*All coverage is approximate and depend upon substrate, details and individual application*

#### Packaging/Shelf Life/Storage

Packaging: 5 gallon (19 L) pail

Shelf Life: 2 years

Storage: Protect from extreme heat - 90°F (32°C), freezing and direct sunlight.

#### Technical Data

Water Vapor Transmission: 26 perms

Elongation: 307%

SuperiorCote E-Flex Tensile Bond @ Break: 84 psi

SuperiorCote E-Flex Substrate Bond: 316 psi\* \*substrate failure

Mildew Resistance, ASTM D3273: Pass

Freeze/Thaw ASTM E2485 (Method B): No deleterious effects after 10 cycles - Pass

Wind Driven Rain ASTM D6904 - Pass

Solids by Weight: 59.5

Solids by Volume: 45.4

## APPLICATION PROCEDURE

Priming—Prime new surfaces such as concrete, masonry and stucco with Master Wall Primecoat to equalize substrate absorption. Priming is not necessary over Master Wall Superior Finishes.

Mixing - Thoroughly stir SuperiorCote E-Flex into a homogenous consistency. Small amounts of clean, potable water may be added to obtain a workable consistency. Do not over mix. Do not exceed 12 ounces (0.35L) of water per pail. Do not add accelerators or retarders to SuperiorCote E-Flex.

Application – SuperiorCote E-Flex can be applied by brush, roller, or airless spray equipment. When using a roller, a maximum ¾" nap is recommended. Apply SuperiorCote E-Flex in an even, continuous coat, maintaining a wet edge of 20 mils wet for a dry thickness of 10 mils in one to two-coats with no pinholes.

## CLEAN UP

Tools and equipment can be cleaned with soapy water when SuperiorCote E-Flex is wet.

## LIMITATIONS

Do not use SuperiorCote E-Flex as a finish directly over any Master Wall base coat.

## FOR PROFESSIONAL RESULTS

Apply finish coats away from direct sunlight. Cold joints or color variations can occur if the finish dries too quickly. Under certain conditions dark colors may show efflorescence on the surface during the cure process.

Surfaces exposed to the weather must be sloped (6:12 minimum).

Deep, intense colors should be specified with DuroTone pigments to maintain colorfastness longer. Verify specialty colors with your Master Wall® Distributor.

Information contained in this product data sheet conforms to the standard detail recommendations and specifications for the installation of Master Wall Inc.® products and is presented in good faith. Master Wall Inc.® assumes no liability, expressed or implied as to the architecture, engineering, or workmanship of any project. This information may be concurrent with, or superseded by other applicable documents, such as specifications and details. Contact Master Wall Inc.® for the most current product information. ©2025 Master Wall Inc.®



**Hazard:** This chemical is not considered hazardous according to the OSHA Hazard Communication Standard 2012 (29 CFR 1910.1200).

**VOC:** Less than 50 g/L.

### Approved Substrates

Master Wall® Textured Finishes  
Stucco  
Brick  
Concrete  
Masonry  
Others approved in writing

## APPLICATION TECHNIQUES

*Spray* - Changes in pressures and tip sizes may be needed for proper spray characteristics.

Reducer: No reduction necessary, see mixing instructions if water is added.

Airless Spray: Pressure 2000-2700 p.s.i.  
Tip .021 inch

*Brush* - Use a nylon/polyester brush.

*Roller Cover* - Use a 1/2 to 1-1/2 inch nap synthetic cover. The substrate and its condition will determine the application procedure.

Considerations to minimize pinholes:

- 2-coat application with overnight drying between coats.
- Spray application with backrolling.
- Power rolling.
- Do not paint in direct sun or on a hot surface.
- Do not reduce.

## LIMITED WARRANTY

This product is subject to a written limited material or system warranty. Obtain a warranty from the Tools and Technical tab of our website. Refer to Specifications for more complete information on proper use and handling of this product.