



Master Wall Inc.
Building a Culture of Excellence

PRODUCT DATA

WOOD GRAIN TEX

CIFS® WOOD GRAIN SPECIALTY FINISH

Wood Grain Tex finish recreates the subtle imperfections of a wood finish using plastering techniques. The easily applied texture highlights wall surfaces with a very subtle nuances that when combined with our Glaze and Sealer recreates the look of wood without all the negative aspects.

FEATURES & BENEFITS

- Ready to Use
- Ultra-thin applications (two thin coats)
- Cost effective
- Tintable
- Accented with Wood Grain Glaze and Sealer

Application Temperature: 40° -110°F (5° -43°C)

Working Time: 1/2 hour

Dry Time: 24 hours at room temperature, working and drying time will vary with temperature and humidity.

JOB CONDITIONS

Air and substrate temperature for application must be 40°F (5°C) or higher and must remain 40°F (5°C) or higher for a minimum of 24 hours. Provide temporary protection to protect the wall system from damage until permanent flashings, caps and sealants are installed. Store materials within prescribed temperature limits and out of direct sunlight. High temperatures will reduce working times, Low temperatures and/or high humidity and pigment loading will extend working, set and dry times.

PREPARATION

Master Wall® base coat shall be clean, dry, smooth, and free of any mesh pattern with desired wood grain grooves already added.

Mixing – Open pail of Wood Grain Tex and mix approximately one minute with a fixed wheel type paddle or equivalent mixing blade attached to a 1/2" (13 mm) heavy duty drill at 400-500 rpm. Small additions of water, up to 240 ml (8 oz.) per pail, may be added for workability as needed.

Coverage per pail (sf/sm)*

175-200 sf (16-18.6 sm) in a two-coat application process

**All coverage is approximate and depend upon substrate, details and individual application*

Packaging/Shelf Life/Storage

Packaging: 5 gallon (19L) pail

Shelf Life: 2 years

Storage: Protect from extreme heat - 90°F (32°C), freezing and direct sunlight.

Hazard: This chemical is not considered hazardous according to the OSHA Hazard Communication Standard 2012 (29 CFR 1910.1200).

VOC: Less than 10 g/L.

See Superior Finishes for other technical properties

Approved Substrates

Master Wall® Base Coats
Others approved in writing

APPLICATION PROCEDURE

Using a Wind-Lock T-VPF2008, T-VPF2411 or T-VPF2812 Stainless Steel Venetian Plaster Trowel apply a very tight, thin coat of Wood Grain Tex to the surface free of trowel marks. Use moderate to high pressure with a trowel angle of about 60-80 degrees to the wall surface. The amount of material applied to the wall surface is paper thin. Allow the Wood Grain Tex to take up for 2-3 hours or until fully set up. Clean the surface to remove any dust.

Apply a second coat of Wood Grain Tex. Trowel to a level surface and remove excess material. Immediately after troweling, using a plastic float, float the Wood Grain Tex in the direction of the intended "grain" of the wood. Once dry, lightly sand in the direction of the grain with 100-grit sandpaper to remove excess material and create a level surface for Wood Grain Glaze application.

Note: Application problems occur when Wood Grain Tex is applied too thick. Only paper-thin applications are necessary. Surface may be coated after 24 hours with Master Wall® Wood Grain Sealer. Follow individual data sheet instructions for products selected.

CAUTIONS AND LIMITATIONS

- Wood Grain Tex is not intended for deep depressions or irregular surfaces.
- Slope all exterior surfaces 1:2 minimum to shed water.
- Apply in paper thin applications, shrinkage, cracking, or blistering can occur over 1/16" (1.6 mm) thick.
- Application in direct sunlight may affect aesthetics if the Wood Grain Tex dries too quickly. Avoid direct sunlight.
- When cleaning do not use harsh or abrasive cleaners. Wash gently using a soap and water solution followed by a warm water rinse.

CLEAN UP

Tools and equipment can be cleaned with soapy water while the Wood Grain Tex is still wet.

Information contained in this product data sheet conforms to the standard detail recommendations and specifications for the installation of Master Wall Inc.® products and is presented in good faith. Master Wall Inc.® assumes no liability, expressed or implied as to the architecture, engineering, or workmanship of any project. This information may be concurrent with, or superseded by other applicable documents, such as specifications and details. Contact Master Wall Inc.® for the most current product information. ©2023 Master Wall Inc.®



Health & Safety

WARNING!

Causes eye and skin irritation.

Precautionary Statement

Wash hands thoroughly after handling. Wear protective gloves/protective clothing/eye protection/face protection.

FIRST AID MEASURES

Eye Contact: Immediately flush eyes with plenty of water for at least 15 to 20 minutes. Ensure adequate flushing of the eyes by separating the eyelids with fingers. Get immediate medical attention.

Skin Contact: Immediately wash skin with plenty of soap and water for 15 to 20 minutes, while removing contaminated clothing and shoes. Get medical attention if irritation develops or persists.

Inhalation: If inhaled, remove to fresh air. If not breathing, give artificial respiration or give oxygen by trained personnel. Seek immediate medical attention.

Ingestion: If swallowed, do NOT induce vomiting. Call a physician or poison control center immediately. Never give anything by mouth to an unconscious person.

Store locked up. Dispose of contents/container in accordance with Local, State, Federal and Provincial regulation.

Spills: Collect with suitable absorbent material such as cotton rags.

Disposal: Dispose of in accordance with local, state or federal regulations.

Warning: KEEP CONTAINER CLOSED WHEN NOT IN USE. KEEP OUT OF THE REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY.

Consult the Safety Data Sheet (SDS) in the Products section at masterwall.com for further health and safety information.

LIMITED WARRANTY

This product is subject to a written limited material or system warranty. Obtain a warranty from the Tech Support tab of our website. Refer to Specifications for more complete information on proper use and handling of this product.